

The Cleaning and Maintenance of CONFORM[®] walls depends on the extent of the dirt or damage to the walls.

1. General Cleaning

- Water and a stiff brush or 3" scraper are used to soften and remove any dirt deposits or concrete residue from the surface of the CONFORM[®] components.
- The Nuform degreaser, diluted 1:4 with water, and clean rags are used to remove any film of dirt or grease.

2. Deep Scratch Repair

- Deep scratches are repaired with the Nuform patching compound as specified in Construction Bulletin # 7.

3. Light Scratch Repair

- Polishing Compound and a 7" variable speed Angle Polisher with a polishing pad are used to polish the surface until light scratches are no longer visible.
- Rubbing compounds are NOT recommended since they will scratch the surface.
- Orbital polishers are NOT recommended since they are less effective

4. Surface Sheen

- Finish Wax and a 7" variable speed Angle Polisher or Grinder with a buffer pad are used to wax and shine the surface until the luster is restored.

5. Materials and Equipment

- Polishing Compound and Finish Wax as manufactured by Mother's, Simoniz and Turtle Wax for automotive car care are suitable.
- A 7" variable speed Angle Polisher and pads as manufactured by Porter Cable, Makita and DeWalt for automotive car care are suitable.